

各種硬度の換算表

ビッカース硬度	ブリネル硬度	ロックウエル 硬度 B スケール	ロックウエル 硬度 C スケール	ショア硬度
50	47	-		
60	55	10.0		
70	63	24.5		
80	72	37.5		
85	81	41.0	-	-
90	86	48.0	-	-
95	90	52.0	-	-
105	95	56.2	-	-
110	105	62.3	-	-
120	114	66.7	-	-
130	124	71.2	-	20
140	133	75.0	-	21
150	143	78.7	-	22
160	152	81.7	0.0	24
170	162	85.0	3.0	25
180	171	87.1	6.0	26

190	181	89.5	8.5	28
200	190	91.5	11.0	29
210	200	93.4	13.4	30
220	209	95.0	15.7	32
230	219	96.7	18.0	33
240	228	98.1	20.3	34
250	238	99.5	22.2	36
260	247	101.0	24.0	37
270	256	102.0	25.6	38
280	265	103.5	27.1	40
290	275	104.5	28.5	41
300	284	105.5	29.8	42
310	294	-	31.0	-
320	303	107.0	32.2	45
330	313	-	33.3	-
340	322	108.0	34.4	47
350	331	-	35.5	-
360	341	109.0	36.6	50
370	350	-	37.7	-
380	360	110.0	38.8	52
390	369	-	39.8	-

400	379	-	40.8	55
410	388	-	41.8	-
420	397	-	42.7	57
430	405	-	43.6	-
440	415	-	44.5	59